



Making Aircraft Quieter, Safer and More Comfortable.
 5000 North Highway 251, Davis Junction, IL 61020 | 800 945 7135 | www.skandiainc.com

VERTICAL FLAMMABILITY TEST RESULTS			Skandia, Inc WO# 337148-18		
14 CFR Part 25.853 (a) Amdt 25-116 Appendix F Part I (a)(1)(ii)			Client PO 12418		
Industrial Energy Products Inc 56 Newcomer Road Mount Joy PA 17552 US			Doc ID 12NW-395559 Test Plan # Rev Project # Technician Crystal Coleman		
AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION					
Make: stock		Model:		Serial: Tail:	
Conditioning Room Data: Date In: 01/25/2018 Time In: 10:45 AM Date Out: 01/26/2018 Time Out: 1:08 PM					
SPECIMEN MATERIALS					
Part No: HSL EVO FCB STORAGE BAG Industrial Energy Products, Inc.: Plastic, Blue, Ref # HSL EVO FCB STORAGE BAG					
Lot No: 20172018 STBG					
Test Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drippings (seconds)	
1	12	3.0	3.3	0.0	
2	12	0.0	2.0	0.0	
3	12	3.0	1.8	0.0	
Average:		2.0	2.4	0.0	
<i>Vertical (12 second) Burn Test: Average Self-Extinguish time may not exceed 15 seconds. Average Burn Length may not exceed 8 inches. Average Dripping may not exceed 5 seconds after falling.</i>					
Comments:					
<input checked="" type="checkbox"/> Passed <input type="checkbox"/> Failed					
CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.					
Crystal Coleman <i>Crystal Coleman</i>			01/26/2018		
WITNESS			DATE		