



Making Aircraft Quieter, Safer and More Comfortable.  
 5000 North Highway 251, Davis Junction, IL 61020 | 800 945 7135 | www.skandiainc.com

<b>VERTICAL FLAMMABILITY TEST RESULTS</b>	Skandia, Inc WO# 336952-18
14 CFR Part 25.853 (a) Amdt 25-116 Appendix F Part I (a)(1)(i)	Client PO
Industrial Energy Products Inc 56 Newcomer Road Mount Joy PA 17552 US	Doc ID 60NW-395329 Test Plan # Rev Project # Technician Matt Ray

**AIRCRAFT OR AIRCRAFT COMPONENT IDENTIFICATION**

Make: stock	Model:	Serial:	Tail:
-------------	--------	---------	-------

Conditioning Room Data: Date In: 01/23/2018 Time In: 10:20 AM Date Out: 01/24/2018 Time Out: 1:12 PM

**SPECIMEN MATERIALS**

Part No: **HSL FCB Gen 2 Gloves**  
 Industrial Energy Products, Inc.: Gloves, Red Hot Face, Ref # HSL FCB Gen 2 Gloves

Lot No: 201718G2


Test Set	Flame Application (seconds)	Flame Time (seconds)	Burn Length (inches)	Drippings (seconds)
1	60	2.0	1.5	0.0
2	60	3.0	1.5	0.0
3	60	2.0	1.4	0.0
Average:		2.3	1.5	0.0

*Vertical (60 second) Burn Test: Average Self-Extinguish time may not exceed 15 seconds.  
 Average Burn Length may not exceed 6 inches. Average Dripping may not exceed 3 seconds after falling.*

Comments:

**Passed**     **Failed**

CERTIFICATION: I certify that after testing these specimens, the above results were obtained in accordance with the procedures and equipment specified by Code of Federal Regulations Title 14 Part 25, or the Aircraft Materials Fire test handbook. Not FAA approved unless an 8110-3 has been issued.

Matt Ray  WITNESS	01/24/2018 DATE
---	--------------------